

| PRODUCT | % VISIBLE LIGHT TRANSMISSION (VLT) | % TOTAL SOLAR TRANSMITTANCE | % TOTAL SOLAR REFLECTANCE | % TOTAL SOLAR ABSORBANCE | % VISIBLE LIGHT REFLECTANCE INT | % VISIBLE LIGHT REFLECTANCE EXT | WINTER U-VALUE | % UV REJECTED | % GLARE REDUCTION | SHADING COEFFICIENT | % TOTAL SOLAR ENERGY REJECTED (TSER) |
|-----------------------------|------------------------------------|-----------------------------|---------------------------|--------------------------|---------------------------------|---------------------------------|----------------|---------------|-------------------|---------------------|--------------------------------------|
| Anti-Graffiti Series | | | | | | | | | | | |
| 4M Anti-Graffiti | 86 | 78 | 9 | 13 | 9 | 9 | 1.09 | 95 | 3 | 0.93 | 19 |
| 6M Anti-Graffiti | 86 | 76 | 10 | 14 | 10 | 10 | 1.09 | 95 | 3 | 0.93 | 19 |

PHYSICAL PROPERTIES

| PRODUCT | FILM THICKNESS | SINGLE OR MULTI-PLY | TENSILE STRENGTH | BREAK STRENGTH | ELONGATION AT BREAK | PEEL STRENGTH | PUNCTURE STRENGTH |
|-----------------------------|----------------|---------------------|------------------|----------------|---------------------|---------------|-------------------|
| Anti-Graffiti Series | | | | | | | |
| 4M Anti-Graffiti | 0.004" | Single | 34,900 psi | 136 lbs/inch | >100% | 1000 g/inch | 93 lbs |
| 6M Anti-Graffiti | 0.006" | Multi | 32,200 psi | 190 lbs/inch | >100% | 1000 g/inch | 132 lbs |