

| PRODUCT | % VISIBLE LIGHT TRANSMISSION (VLT) | % TOTAL SOLAR TRANSMITTANCE | % TOTAL SOLAR REFLECTANCE | % TOTAL SOLAR ABSORBANCE | % VISIBLE LIGHT REFLECTANCE INT/EXT | WINTER U-VALUE | % UV REJECTED | % GLARE REDUCTION | SHADING COEFFICIENT | SOLAR HEAT GAIN COEFFICIENT | % TOTAL SOLAR ENERGY REJECTED (TSER) |
|-------------------------|------------------------------------|-----------------------------|---------------------------|--------------------------|-------------------------------------|----------------|---------------|-------------------|---------------------|-----------------------------|--------------------------------------|
| Specialty Series | | | | | | | | | | | |
| 2 Mil White Matte | 64 | 58 | 17 | 25 | 21 / 21 | 1.03 | 99 | 28 | 0.76 | 0.66 | 34 |
| White Out | 15 | 18 | 67 | 15 | 85 / 85 | 1.03 | 99 | 83 | 0.25 | 0.22 | 78 |
| Black Out | 0 | 0 | 5 | 95 | 6 / 6 | 1.02 | 100 | 100 | 0.32 | 0.28 | 72 |
| Crystal PET | 84 | 76 | 15 | 9 | 19 / 19 | 0.95 | 99 | 7 | 0.91 | 0.79 | 21 |
| Crystal Vinyl | 87 | 80 | 9 | 11 | 10 / 11 | 1.04 | 75 | 3 | 0.96 | 0.83 | 17 |
| DRMDS 7 / PS 7 | 7 | 6 | 53 | 41 | 14 / 60 | 0.91 | 99 | 94 | 0.18 | 0.16 | 84 |
| SLYRDS 10 | 10 | 9 | 20 | 71 | 14 / 15 | 0.99 | 99 | 89 | 0.32 | 0.28 | 72 |
| 4M Anti-Graffiti | 86 | 78 | 9 | 13 | 9 / 90 | 1.09 | 95 | 3 | 0.93 | 0.81 | 19 |
| 6M Anti-Graffiti | 86 | 76 | 10 | 14 | 10 / 10 | 1.09 | 95 | 3 | 0.93 | 0.81 | 19 |