

PRODUCT	% VISIBLE LIGHT TRANSMISSION (VLT)	% TOTAL SOLAR TRANSMITTANCE	% TOTAL SOLAR REFLECTANCE	% TOTAL SOLAR ABSORBANCE	% VISIBLE LIGHT REFLECTANCE INT/EXT	WINTER U-VALUE	% UV REJECTED	% GLARE REDUCTION	SHADING COEFFICIENT	SOLAR HEAT GAIN COEFFICIENT	% TOTAL SOLAR ENERGY REJECTED (TSER)
Specialty Series											
2 Mil White Matte	64	58	17	25	21 / 21	1.03	99	28	0.76	0.66	34
White Out	15	18	67	15	85 / 85	1.03	99	83	0.25	0.22	78
Black Out	0	0	5	95	6 / 6	1.02	100	100	0.32	0.28	72
4M Anti-Graffiti	86	78	9	13	9 / 9	1.09	95	3	0.93	0.81	19
6M Anti-Graffiti	86	76	10	14	10 / 10	1.09	95	3	0.93	0.81	19
DRMDS 7/PS 7	7	6	53	41	14 / 60	0.91	99	94	0.18	0.16	84
SYLRDS 10	10	9	20	71	14 / 15	0.99	99	89	0.32	0.28	72