

	% VISIBLE LIGHT TRANSMISSION (VLT)	% TOTAL SOLAR TRANSMITTANCE	% TOTAL SOLAR REFLECTANCE	% TOTAL SOLAR ABSORBANCE	% VISIBLE LIGHT REFLECTANCE INT	% VISIBLE LIGHT REFLECTANCE EXT	WINTER U-VALUE	% UV REJECTED	% GLARE REDUCTION	SHADING COEFFICIENT	% TOTAL SOLAR ENERGY REJECTED (TSER)	
Silver Series (Reflective, Silver)												
4MSilver20	15	12	55	33	58	60	0.94	99	84	0.24	79	
8MSilver20	15	12	55	33	58	60	0.94	99	84	0.24	79	

PHYSICAL PROPERTIES

PRODUCT	FILM THICKNESS	SINGLE OR MULTI-PLY	TENSILE STRENGTH	BREAK STRENGTH	ELONGATION AT BREAK	PEEL STRENGTH	PUNCTURE STRENGTH
Silver Series (Reflective, Silver)							
4MSilver20	0.004"	Multi	33,600 psi	134 lbs/inch	>100%	2750 g/inch	103 lbs
8MSilver20	0.008"	Multi	30,400 psi	265 lbs/inch	>100%	2750 g/inch	173 lbs