

PRODUCT	% VISIBLE LIGHT TRANSMISSION (VLT)	% TOTAL SOLAR TRANSMITTANCE	% TOTAL SOLAR REFLECTANCE	% TOTAL SOLAR ABSORBANCE	% VISIBLE LIGHT REFLECTANCE INT	% VISIBLE LIGHT REFLECTANCE EXT	WINTER U-VALUE	% UV REJECTED	% GLARE REDUCTION	SHADING COEFFICIENT	% TOTAL SOLAR ENERGY REJECTED (TSER)
Symphony™ Series (Dual-Reflective, Neutral)											
4MSY65	65	54	10	36	11	14	1.04	99	27	0.74	35
4MSY35	35	27	27	46	18	25	1.07	99	58	0.46	60
6MSY35	35	27	27	46	18	25	1.07	99	58	0.46	60
6MSY25	27	19	36	45	20	35	1.03	99	70	0.38	67
8.5MSY50	47	36	19	45	12	16	1.09	99	48	0.60	48
8.5MSY35	35	27	27	46	18	25	1.07	99	58	0.46	60
8.5MSY25	27	19	36	45	20	35	1.03	99	70	0.38	67

PHYSICAL PROPERTIES

PRODUCT	FILM THICKNESS	SINGLE OR MULTI-PLY	TENSILE STRENGTH	BREAK STRENGTH	ELONGATION AT BREAK	PEEL STRENGTH	PUNCTURE STRENGTH
Symphony™ Series (Dual-Reflective, Neutral)							
4MSY65	0.004"	Multi	33,600 psi	134 lbs/inch	>100%	2750 g/inch	103 lbs
4MSY35	0.004"	Multi	33,600 psi	134 lbs/inch	>100%	2750 g/inch	103 lbs
6MSY35	0.006"	Multi	32,200 psi	190 lbs/inch	>100%	2750 g/inch	132 lbs
6MSY25	0.006"	Multi	32,200 psi	190 lbs/inch	>100%	2750 g/inch	132 lbs
8.5MSY50	0.0085"	Multi	30,400 psi	265 lbs/inch	>100%	2750 g/inch	173 lbs
8.5MSY35	0.0085"	Multi	30,400 psi	265 lbs/inch	>100%	2750 g/inch	173 lbs
8.5MSY25	0.0085"	Multi	30,400 psi	265 lbs/inch	>100%	2750 g/inch	173 lbs