

PRODUCT	% VISIBLE LIGHT TRANSMISSION (VLT)	% TOTAL SOLAR TRANSMITTANCE	% TOTAL SOLAR REFLECTANCE	% TOTAL SOLAR ABSORBANCE	% VISIBLE LIGHT REFLECTANCE INT	% VISIBLE LIGHT REFLECTANCE EXT	WINTER U-VALUE	% UV REJECTED	% GLARE REDUCTION	SHADING COEFFICIENT	% TOTAL SOLAR ENERGY REJECTED (TSER)
Ultra-Vision™ Series (Spectrally Selective, Neutral)											
8.5MULV40	38	29	22	49	14	17	1.04	99	57	0.46	60

PHYSICAL PROPERTIES

PRODUCT	FILM THICKNESS	SINGLE OR MULTI-PLY	TENSILE STRENGTH	BREAK STRENGTH	ELONGATION AT BREAK	PEEL STRENGTH	PUNCTURE STRENGTH
Ultra-Vision™ Series (Spectrally Selective, Neutral)							
8.5MULV40	0.0085"	Multi	30,400 psi	265 lbs/inch	>100%	2750 g/inch	173 lbs